

**DESCRIPTION**

Kraft facing is Extensible Kraft paper coated on one side with a thermoplastic asphalt coating. The asphalt coating is used to bond fiberglass insulation to the facing in a subsequent manufacturing process. The uncoated side is normally printed with the manufacturer's logo (available upon request).

**APPLICATION**

This product is typically used as a facing for residential building applications.

**CONSTRUCTION**

Basis Weight	17.6 lbs/MSF (85.9 g/m <sup>2</sup> )
Extensible Kraft paper	35 lbs/3000 ft <sup>2</sup> (57 g/m <sup>2</sup> )
Asphalt Coating	Full Coat



**SPECIFICATIONS**

Properties	Test Method	
Permeance (MVTR)	ASTM E96	1.0 max perms
Tensile Strength	ASTM D828	MD: 21.0 lbs/in (3.7 N/mm) XD: 10.5 lbs/in (1.8 N/mm)
Tear	TAPPI-T414	MD: 53.0 g/min XD: 57.0 g/min
Mold Resistance	ASTM C1338	Pass



717 17th St.  
Denver, CO 80202  
(800) 654-3103  
JM.com

**Hamilton Technologies**  
7400 Ranco Rd.  
Richmond, VA 23228  
804-261-7400

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of the product listed herein represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Any references to numerical flame spread or smoke developed ratings are not intended to reflect hazards presented by these or any other materials under actual fire conditions. Check with the Regional Sales Office nearest you for current information.

**All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on other Johns Manville thermal insulation and systems, visit [www.jm.com/terms-conditions](http://www.jm.com/terms-conditions) or call (800) 654-3103.**