

StarStran® 719

CHOPPED
STRANDS

Product description:

StarStran® chopped strands with 719 sizing are produced by chopping E-glass fibers coated with a silane based sizing.

StarStran® 719 has been specifically designed as a highly effective reinforcement for polyamides.

Benefits:

- Excellent matrix bonding in polyamides
- Outstanding strand integrity
- Effective fiber dispersion
- Optimal fiber distribution

Resin compatibility:

- Polyamide resins (PA66, PA6)
- PET
- PVC
- PVA
- TPU



Designation: Glass type is E-Glass

JM Designation	Region	Filament Diameter (µm)	Sizing Designation	Chopped Strands Length (inches)
StarStran® 719 14 1/8"	NA	14	719	1/8"

Packaging:

Region	Packaging Type	Pallet dimensions	Net Weight per pallet	Bag per pallet
NA	Bulk Bag	45" x 45"	1800 lbs	1

Storage:

These products should be stored in original packaging in dry, roofed, dust free storehouses. The recommended temperature is between 10°C to 30°C (50°F to 86°F). The products should remain in the original packaging and be conditioned in the work area for a minimum of 24 hours prior to use. The pallets should be single stacked unless otherwise specified on the packaging unit.

**Warranty disclaimer :**

Technical specifications as shown in this literature are intended to be used as general guidelines only. Please refer to the Safety Data Sheet and product label prior to using this product. The physical and chemical properties of this product represent typical, average values obtained in accordance with accepted test methods and are subject to normal manufacturing variations. They are supplied as a technical service and are subject to change without notice. Check with the Regional Sales Office nearest you for the most current information.

All Johns Manville products are sold subject to Johns Manville's standard Terms and Conditions, which includes a Limited Warranty and Limitation of Remedy. For a copy of the Johns Manville standard Terms and Conditions or for information on Johns Manville products, please visit <https://www.jm.com/en/login/policies-terms-and-conditions/> or call (800)654-3103.

Values:

All data represent typical average values.

**US Headquarters**

Johns Manville
717 17th Street
Denver, CO 80202 - USA
Phone: +1 (303) 978 2000

Customer-Service-Offices:**North America**

Johns Manville
7500 Dutch Road
Waterville, OH 43566 - USA
Phone: +1 (800) 554 4826

Europe

Johns Manville Slovakia, a.s.
Strojársená 1
91799 Trnava - Slovakia
Phone: +421 (0) 33 5918 249

www.jm.com

fibers@jm.com